



INDUSTRIES, INC.




INDUSTRIES, INC.
 P.O. BOX 390037
 3730 SALEM ST.
 DENVER, COLO. 80239
 (303) 371-3950 DENVER
 (307) 237-3719 CASPER



FAX (303) 371-3959

WELDED WIRE FABRIC STOCKED STYLES

STYLE	WT/CSF
6 x 6 - W1.4 x W1.4 (6 x 6 - 10/10)	21
6 x 6 - W2.1 x W2.1 (6 x 6 - 8/8)	29
6 x 6 - W2.9 x W2.9 (6 x 6 - 6/6)	42
6 x 6 - W4.0 x W4.0 (6 x 6 - 4/4)	58
4 x 4 - W2.9 x W2.9 (4 x 4 - 6/6)	62
4 x 4 - W4.0 x W4.0 (4 x 4 - 4/4)	85



BAR LAPS (1-0 MIN.)

DIA	# 2	# 3	# 4	# 5	# 6	# 7	# 8	# 9	# 10	# 11
24	1-0	1-0	1-0	1-3	1-6	1-9	2-0	2-4	2-7	2-10
30	1-0	1-0	1-3	1-7	1-11	2-3	2-6	2-10	3-3	3-7
36	1-0	1-3	1-6	1-11	2-3	2-8	3-0	3-5	3-10	4-3
40	1-0	1-3	1-8	2-1	2-6	2-11	3-4	3-10	4-3	4-9
48	1-0	1-6	2-0	2-6	3-0	3-6	4-0	4-7	5-1	5-8

ASTM STANDARD REINF. BARS

IMPERIAL/ SOFT METRIC	WT/FT.	DIAMETER	CROSS-SEC AREA \square
* #2/	.167	.250	.05
#3 / #10	.376	.375	.11
#4 / #13	.668	.500	.20
#5 / #16	1.043	.625	.31
#6 / #19	1.502	.750	.44
#7 / #22	2.044	.875	.60
#8 / #25	2.670	1.000	.79
#9 / #29	3.400	1.128	1.00
#10 / #32	4.303	1.270	1.27
#11 / #36	5.313	1.410	1.56
#14 / #43	7.650	1.693	2.25
#18 / #57	13.60	2.257	4.00

*PLAIN ROUND
 #6 THRU #18 NOT STOCKED IN GRADE 40

AMERICAN STANDARD BAR MARKS
 Lower Strength Bars Show Only 3 Marks (no grade mark)
 1st-Producing Mill (usually an initial)
 2nd-Bar Size Number (#3 through #18)
 3rd-Type (~~N~~ for New Billet, ~~A~~ for Axle, ~~I~~ for Rail)
 High Strength Bars Must Also Show Grade Marks
 60 or One (1) Line for 60,000 psi Strength
 (Grade mark lines are smaller and between the two main ribs which are on opposite sides of all American Bars)

CONTINUOUS LINE SYSTEM-GRADE MARKS

